

enMAGIC

DESCRIPTION: enMAGIC is trowel-grade polymer modified cementitious micro topping used for smoothing concrete countertops and creating interesting effects. enMAGIC may be integrally colored, stained, sanded, sandblasted, scored, stenciled and sealed like plain concrete. enMAGIC is packaged in a one gallon buckets in white and gray.

SURFACE PREPARATION: Insure that the surface is clean, dry and free of grease, oil, and sealers prior to applying enMAGIC to a hardened concrete countertop surface.

MIXING: Mix enMAGIC with 18 oz to 24 oz of clean water depending upon the desired consistency. Mix by hand or with small drill in a one gallon bucket.

APPLICATION: Work with application techniques to gain confidence and familiarity. Dampen the substrate with water, pour the enMAGIC in a long thin line. Spread with a margin trowel, pool trowel, Magic Trowel or squeegee. Apply as thin as possible.

COLORING: Create samples to determine the rate of enCOLOR addition or to determine acid stain dilution rates.

SEALING: enMAGIC may be treated with any concrete sealer or wax, however enPOXY provides a superior stain and abrasion resistance.

LIMITATIONS: enMAGIC is a thin build product, avoid thickness of greater than 1/8". Do heavy patching and filling of deep holes prior to applying enMAGIC. CAUTION: Contact with water may cause uncured enMAGIC to delaminate.

TECHNICAL DATA:

| | |
|------------------------------|---|
| Coverage..... | 200 – 400 sq. ft/gallon |
| Drying time (re-coat)..... | 4 hours at 72°F |
| Drying time (staining)..... | Overnight |
| Clean up..... | Warm, soapy water before material hardens |
| Nonvolatile content..... | 47% (+/-)0.5 |
| pH..... | 0.5 – 11.5 |
| Bulk density..... | 8.2 lbs/gal |
| Application temperature..... | Above 45° F |

CAUTION: Keep out of reach of children!



Distributed by Cimarron Wholesale
125 NE 40th Street
Oklahoma City, OK 73105 USA
Phone 866-906-2006 / Fax 405-526-2008
www.encountertop.com